Data Sheet C-HE10-PE07-S




LED Hiding Diffuser

Symmetric LED hiding film for excellent smoothing, lamp hiding, and color mixing in Lighting applications

Optical Properties

*Efficiency 93 - 96% FWHM Diffusion $8.2^{\circ} \pm 1^{\circ}$



Substrate Properties

Substrate Material PET Measurement Method **Thickness** 0.21 mm / 7 mil Micrometer 1.4 g/cm³ ASTM D792 Density Elongation (MD/TD) 215/140% **ASTM D882** Tensile (MD/TD) 23.5/26 Kpsi ASTM D882 Min Bend Radius 12.7 mm ASTM D522 Heat/Shrink (MD/TD) <1.0/0.5% **ASTM D1204** Backside Smooth

Environmental

| Condition | Duration/Cycles | Δ Transmission | ΔE* | Measurement Method |
|--------------------|-----------------|-----------------------|-----|------------------------------|
| -40 °C | 1000 Hours | <0.5% | <1 | |
| 105 °C | 1000 Hours | <0.5% | <2 | Measurements Following |
| Cycle -40 to 85 °0 | C 100 Cycles | <0.5% | <1 | CIE 1931 (D65, 10°) Standard |
| 65 °C/95% RH | 1000 Hours | <0.5% | <1 | |

Measurement results are the change compared to intitial values, and are representative of typical measured results. $E^* = V(L^{*2} + a^{*2} + b^{*2})$

Data Sheet Version: M BrightView Technologies Confidenital Information

Product Version: M

Date generated: Tuesday, July 8, 2025

Database Version: v24.2.21

www.brightviewtech.com Sales@brightviewtech.com

+1 919-228-4370

Data Sheet C-HE10-PE07-S



Ratings and Certifications

BrightView Technologies' manufacturing facilities are ISO9001:2015 certified by Orion Registrar, Inc.

This product is RoHS Compliant (certificate available upon request). Product is non-halogenated.

The substrate material used in this product has the following properties as provided by the vendor. Yellow cards for these substrates are available. BrightView diffusers have not been tested or rated by UL. The material safety data sheets for substrate materials are available upon request.

• UL-94 rating of substrate material: VTM-2

• UL RTI Elec: 105 Imp: 105 Str: 105

Quality

- If purchasing full sheets, the central 24 in (610 mm) x 48 in (1219 mm) or 72in (1830 mm) is defined as "quality area" which meets all specification, material ouside the quality area should not be used.
- Inspected according to BrightView Inspection Method Cosmetic Specifications, document BVT-FGS-001. Document available upon request.


Handling Techniques

- Care should be taken when moving these parts on any surface. The preferred method is to lift the material directly up and off the surface. To avoid scrathing the substrate, do not slide the material across any surface.
- Cotton gloves are recommended while handling films to prevent oil stains or fingerprints.
- Care should be taken to prevent spatter or oil spots from machine lubrication.

BrightView goniometric angle test methods:

- (1) 532 nm laser collimated to 0.5° FWHM
- (2) Input source is white light collimated to 3.4° FWHM
- (3) Input source is white light collimated to 5.3° FWHM

Optical Profile



Data Sheet Version: I BrightView Technologies Confidenital Information

Product Version: M

Date generated: Tuesday, July 8, 2025

Database Version: v24.2.21

+1 919-228-4370

www.brightviewtech.com Sales@brightviewtech.com

^{*}Efficiency measurements are done using a Cree LMR040-0700-27F9-10100TW luminaire in an integrating sphere. (https://cree-led.com/media/documents/LEDmodules LMR4.pdf)